

NATURAL CORKS

TECHNICAL SPECIFICATIONS



| TECHNICAL SPECIFICATIONS | |
|--------------------------|-------------------------------------|
| TEST | SPECIFICATIONS |
| DIMENSIONAL | |
| Length | VN $\pm 1,0$ |
| Diameter | VN $\pm 0,5$ |
| Ovality | $\leq 0,7\text{mm}$ |
| PHYSICAL | |
| Humidity | 4 -8% |
| Visual classification | In compliance with reference sample |
| MECHANICAL | |
| Compression strength | 70 \pm 30daN |
| Extraction strength | 30 \pm 10daN |
| Sealing behaviour | Absence of leakage at 1.5bar |
| Capillarity | < 2mm |
| CHEMICAL | |
| Residual peroxide | $\leq 0.2\text{mg/cork}$ |
| Solid residue | < 1mg/cork |
| Sensory analysis | Absence of foreign odours |

Method NP 4351